## استانداردهای تمایل به کثیفی

## **Laboratory Standards and** Certifications

The Ownership of This Catalog Is Reserved for **Kiliet and Coping Is Prohibited** 



**Kiliet.co** 



info@kiliet.com



www.kiliet.com



## استاندارد تمایل به کثیفی

## استاندارد تمایل به کثیفی

Test No: 123431

Independent of Textile

PO Box 1948 - 1503 East Morris Street - Dalton, GA 30722

Phone: 706-278-3013

Fax: 706-272-7057 •

E-mail: info@ittslab.com

Test Report

Customer: Standard Carpets Ind. LLC

August 13, 2012

Subject: Sample(s) of carpet submitted for testing by the customer and identified below:

Sample Identification: Nylon Carpet Tiles

**Test Method Conducted** AATCC Test Method 16 Option E Colorfastness to Light (Water-Cooled Xenon Arc)

Purpose and Scope

This test method provides the general principles and procedures which are currently in use for determining the colorfastness, to light of textile materials.

Procedure

Samples of the textile material to be tested and the agreed upon comparison standard(s) are exposed simultaneously to a light source under specified conditions. The colorfastness to light of the specimen is evaluated by comparison of the color change of the exposed portion to the masked or control portion of the test specimen using the AATCC Gray Scale for Color Change or by instrumental color measurement.

Test Specimen Identification	Number of Cycles	Rating
See Above	2 (40 AFU's)	5

	Key to Ratings	
5	Negligible or no change	
4	Slight change	J.
3	Noticeable change	
2	Considerable change	ij
1	Severe change	

ent Suddeth

Our letters and reports are for the exclusive use of the customer to whom they are addressed, and their communication to any others or the use of the name of independent Tradile Testing Service, Inc., must receive out prior written approval. Our letters and reports apply only to the sample tested and are not necessarily indicative of the qualities of apparently identical or similar products. The reports and letters and the name of independent Textile Testing Service, Inc., are not to be used under any droumstances in advertising to the general public.

Page 1 of 1

